



BRIDGE H-1442

HAZARDOUS MATERIALS SURVEY

BRIDGE INSPECTION AND SURVEY FOR PRESENCE OF
ASBESTOS AND HEAVY METAL(S),
MAY 2021

NDOT Hazardous Materials Section, Environmental Division

1263 South Stewart Drive
Carson City, NV 89712

EXECUTIVE SUMMARY

The inspection (survey) for hazardous materials was conducted on bridge H-1442 on May 20, 2021, by NDOT personnel from the Hazardous Materials section, of the Environmental Division. The bridge was evaluated for both asbestos containing materials (ACM) and heavy metals in coating materials. One suspect metals sample and nineteen suspect asbestos samples were collected with results and considerations summarized below:

- No ACMs were identified
- No heavy metals were identified in coating materials at regulatory significant concentrations.

1.0 INTRODUCTION

NDOT conducted an asbestos survey and screening for metals-based coating materials on the following bridge structure located in Clark county:

- H-1442 (Mojave Grade Separator, I-515, Las Vegas, NV)

The survey was conducted on May 20, 2021, by NDOT personnel. Suspect Asbestos Containing Material (ACM) were identified and appropriately sampled. Coating materials, if present, were sampled and analyzed for the Resource Recovery and Conservation Act eight (RCRA 8) metals.

Bulk asbestos samples were analyzed by a National Voluntary Laboratory Accredited laboratory by polarized light microscopy (PLM). Metals analysis was conducted by a Nevada Certified Lab. The results of the laboratory analysis are attached as Appendix C and Appendix D, respectively.

2.0 BRIDGE DESCRIPTION

Bridge H-1442 was constructed in 1995 with improvements/maintenance-related activities in 2001. Bridge H-1442 is constructed of concrete components including bridge stem wall/backwall, abutments, wing walls, sound walls, parapet, concrete barriers, and concrete bridge superstructure and deck overlain with asphaltic concrete. White coating material was identified throughout the bridge, various colors of paint on the sound walls, and red paint on abutments. Bridge bearing pads were not located. Rubberized expansion joints were identified.

3.0 FIELD ACTIVITIES

The survey was conducted by NDOT personnel, appropriately licensed Asbestos and Hazardous Emergency Response Act (AHERA) accredited asbestos inspectors. The survey was conducted in general accordance with the sample collection protocols established in EPA regulation 40 CFR 763. A summary of the survey activities performed is discussed below. Copies of AHERA certifications and licenses for NDOT personnel conducting the survey are provided as Appendix E.

3.1 Visual and Physical Assessment

Survey activities began with a visual observation of the structures to identify homogeneous areas of suspect ACM and presence of coating materials. A physical assessment of each homogeneous area of suspect ACM was conducted to assess the friability and condition of the materials.

The homogeneous areas identified during the visual survey, the presence of coating materials, and sample identifiers are summarized in Table 1.

Table 1 - Bridge Component Descriptions

Homogeneous Area	Description	Sample IDs
A	bridge deck	DECK-1, DECK-2, DECK-3
B	sound walls	SW-1, SW-2, SW-3
C	back walls/wing walls	BW/WW-1, BW/WW-2, BW/WW-3
D	parapet	PARA-1, PARA-2, PARA-3
E	beam/superstructure	BEAM-1, BEAM-2, BEAM-3
F	abutment	ABUT-1, ABUT-2, ABUT-3
G	white coating material (composite)	Coating, H-1442 TEXT ^(a)

notes: a) Heavy metals sample identifier.

3.2 Sample Collection

Based on results of the visual observation, bulk samples of suspect ACM and coating materials were collected in general accordance with AHERA sampling protocols. Representative samples of suspect materials were collected in each homogeneous area. Samples were placed in new sealable containers and labeled with unique sample numbers.

3.3 Sample Analysis

Bulk samples of ACM were submitted under chain of custody to Asbestos TEM Laboratories for analysis by PLM. The percentage of asbestos, where applicable, was determined by microscopic visual estimation. Coating material samples were also submitted to Alpha Analytical and analyzed for heavy metals using EPA 6020 test method.

A discussion of suspect ACM and suspect metals-based coating samples collected during the survey and findings are included in Section 6.0.

4.0 PLAN REVIEW

Design plans did not require review.

5.0 REGULATORY OVERVIEW

5.1 Asbestos Regulations

NESHAP (40 CFR Part 61, Subpart M) regulates asbestos fiber emissions and asbestos waste disposal practices. It also requires the identification and classification of existing building materials prior to demolition or renovation activity. Under NESHAP, asbestos-containing building materials are classified as either friable, Category I non-friable, or Category II non-friable ACM. Category I non-friable ACM includes packings, gaskets, resilient floor coverings and asphalt roofing products containing more than 1% asbestos. Category II non-friable ACM are any materials other than Category I materials that contain more than 1% asbestos.

Friable ACM, Category I and Category II non-friable ACM which are in poor condition and have become friable or which will be subjected to drilling, sanding, grinding, cutting or abrading and which could be crushed or pulverized during anticipated renovation or demolition activities are considered Regulated ACM (RACM).

5.2 Coating Material and Lead Based Paint Regulations

Lead-based paint (LBP) is defined as a surface coating or paint containing lead in excess of 0.5% (5000 mg/Kg) by weight (EPA Toxic Substance Control Act, Section 401).

Under EPA regulations heavy metal impacted wastes generated during abatement activities are handled as either a solid waste or a hazardous waste, depending on the concentration of each of the metal(s) and the method of coating material removal.

6.0 FINDINGS AND RECOMMENDATIONS

6.1 Suspect Asbestos Containing Materials

A total of nineteen bulk samples were collected from seven homogeneous areas of suspect ACM. No Asbestos Containing Materials were identified.

A bridge Location Map is included in Appendix A. A photographic log showing homogenous areas is presented in Appendix B. Asbestos analytical results are included in Appendix C. A summary of the suspect ACMs identified is provided in Table 2.

Table 2 – Summary of Suspected ACM

Homogeneous Sampling Area	Sample Number	Material Description/Sample Location	Asbestos Results ⁽¹⁾ , %	NESHAP Category ⁽²⁾	Friability ⁽³⁾
A	DECK-1	bridge deck	Not detected	N/A	non-friable
	DECK-2				
	DECK-3				
B	SW-1	sound walls	Not detected	N/A	non-friable
	SW-2				
	SW-3				
C ⁽⁴⁾	BW/WW-1	back walls/wing walls	Not detected	N/A	non-friable
	BW/WW-2				
	BW/WW-3				
D ⁽⁴⁾	PARA-1	parapet	Not detected	N/A	non-friable
	PARA-2				
	PARA-3				
E ⁽⁴⁾	BEAM-1	beam/super structure	Not detected	N/A	non-friable
	BEAM-2				
	BEAM-3				
F	ABUT-1	abutment	Not detected	N/A	non-friable
	ABUT-2				
	ABUT-3				
G	Coating	white coating material (composite)	Not detected	N/A	non-friable

notes: (1) PLM unless otherwise noted.

(2) NESHAP category I, category II, RACM, or (N/A) not applicable.

(3) Friable materials are those that, when dry, may be crumbled, pulverized, or reduced to powder by hand pressure.

(4) Individual samples split into "Split A" and "Split B" by lab and analyzed due to discrete material differences in sample layers.

Additional suspect materials, other than those identified during the survey, could exist within the structures in areas not accessible to the inspector at the time of the survey. Should suspect materials other than those identified during this survey be uncovered during the renovation/demolition process, those materials should be assumed to be ACM until sampling and analysis can confirm or refute this assumption.

6.2 Coating Materials

One composite sample from the textured coating material found throughout concrete components “H-1442 TEXT” were collected for analysis. This composite sample was analyzed for total arsenic, barium, cadmium, chromium, lead, selenium, silver, and mercury. Based on the EPA’s definition of LBP, the coating material is not a LBP. Analytical results are included in Appendix D and laboratory results are summarized in Table 3.

Table 3 – Summary of Coating Material

Sample Identification	Material Description/Sample Location	Heavy Metal Results ⁽¹⁾ , mg/Kg							
		As	Ba	Cd	Cr	Pb	Se	Ag	Hg
H-1442 TEXT	white coating material (composite)	nd	620	nd	20	10	nd	nd	nd

notes: (1) EPA test method 6020.
nd – not detected above method limits.

6.3 Recommendations

No ACMs were identified. Lead was found in steel component paint but at regulatory insignificant concentrations. Total concentration(s) of the above metal(s) indicates that the coating wastes would not be a toxic characteristic hazardous waste. However, the method used to remove the coating material will need to be taken into consideration prior to disposal.

Appendix A
Bridge Location Map

Bridge H-1442
Mojave Grade Separator, I-515
Las Vegas, Nevada



Appendix B
Bridge Photo Log

PHOTOGRAPHIC DOCUMENTATION
Bridge H-1442
Mojave Grade Separator, I 515
Las Vegas, NV

PHOTO 1

DATE:
05/2/2021

DIRECTION:
North

TAKEN BY:
Rob Piekarz

DESCRIPTION:
Wing and backwall



PHOTO 2

DATE:
05/2/2021

DIRECTION:
Northeast

TAKEN BY:
Rob Piekarz

DESCRIPTION:
Bridge H-1442



PHOTOGRAPHIC DOCUMENTATION
Bridge H-1442
Mojave Grade Separator, I 515
Las Vegas, NV

PHOTO 3

DATE:
05/2/2021

DIRECTION:
East

TAKEN BY:
Rob Piekarz

DESCRIPTION:
Bridge
undercarriage



PHOTO 4

DATE:
05/2/2021

DIRECTION:
South

TAKEN BY:
Rob Piekarz

DESCRIPTION:
Wing and backwall



PHOTOGRAPHIC DOCUMENTATION
Bridge H-1442
Mojave Grade Separator, I 515
Las Vegas, NV

PHOTO 5

DATE:
05/2/2021

DIRECTION:
South

TAKEN BY:
Rob Piekarz

DESCRIPTION:
Bridge H-1442



PHOTO 6

DATE:
05/2/2021


DIRECTION:
Southeast

TAKEN BY:
Rob Piekarz

DESCRIPTION:
Wing and backwall



Appendix C
Asbestos Sample(s)
Analytical Results



ASBESTOS TEM LABORATORIES, INC.

**EPA Method 600/R-93/116
Polarized Light Microscopy
Analytical Report**

Report No. 144570

1350 Freeport Blvd., Unit 104
Sparks, NV 89431
(775) 359-3377
FAX (775) 359-2798

Main Office Located At:
3431 Ettie Street Oakland, CA 94608
Ph. (510) 704-8930 Fax (510) 704-8929



ASBESTOS TEM LABORATORIES, INC



NVLAP Lab Code 200104-0

May-26-21

Robert Piekarz
Nevada Department of Transportation
1263 South Stewart Street
Carson City, NV 89712

RE: LABORATORY JOB No
Polarized light microscopy analytical results for 19 bulk sample(s) with 9 sample split(s)
Job Site: Road milling & bridge repair
Job No.: EA 61010
Report No.: 144570

Enclosed please find the bulk material analytical results for one or more samples submitted for asbestos analysis. The analyses were performed in accordance with EPA Method 600/R-93/116 or 600/M4-82-020 for the determination of asbestos in bulk building materials by polarized light microscopy (PLM). Please note that while PLM analysis is commonly performed on non-friable and fine grained materials such as floor tiles and dust, the EPA method recognizes that PLM is subject to limitations. In these situations, accurate results may only be obtainable through the use of more sophisticated and accurate techniques such as transmission electron microscopy (TEM) or X-ray diffraction (XRD).

Prior to analysis, samples are logged-in and all data pertinent to the sample recorded. The samples are checked for damage or disruption of any chain-of-custody seals. A unique laboratory ID number is assigned to each sample. A hard copy log-in sheet containing all pertinent information concerning the sample is generated. This and all other relevant paper work are kept with the sample throughout the analytical procedures to assure proper analysis.

Each sample is opened in a class 100 HEPA negative air hood. A representative sampling of the material is selected and placed onto a glass microscope slide containing a drop of refractive index oil. The glass slide is placed under a polarizing light microscope where standard mineralogical techniques are used to analyze and quantify the various materials present, including asbestos. The data is then compiled into standard report format and subjected to a thorough quality assurance check before the information is released to the client.

Please note all samples will be held for 3 months from the date of receipt unless otherwise requested by client.

Sincerely Yours,

Laboratory Analyst
ASBESTOS TEM LABORATORIES, INC.

--- These results relate only to the samples tested and must not be reproduced, except in full, with the approval of the laboratory. This report must not be used to claim product endorsement by NVLAP or any other agency of the U.S. Government. ---



NVLAP Lab Code 200104-0

POLARIZED LIGHT MICROSCOPY ANALYTICAL REPORT

EPA Method 600/R-93/116 or 600/M4-82-020

Page: 1 of 3

Contact: Robert Piekarz	Samples Indicated: 19	Report No. 144570
Address: Nevada Department of 1263 South Stewart Street Carson City, NV 89712	Reg. Samples Analyzed: 19	Date Submitted: May-25-21
	Split Layers Analyzed: 9	Date Reported: May-26-21
	Job Site / No. Road milling & bridge repair EA 61010	

SAMPLE ID	ASBESTOS % TYPE	OTHER DATA 1) Non-Asbestos Fibers 2) Matrix Materials 3) Date/Time Collected 4) Date Analyzed	DESCRIPTION
			FIELD LAB
Coating Lab ID # 9092-00059-001	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Calc, Qtz, Other	White coating/texturing materials - throughout bridge
		3) 5-20-21 4) May-26-21	Coating-White
DECK-1 Lab ID # 9092-00059-002	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Calc, Other m.p.	Concrete - bridge surface deck
		3) 5-20-21 4) May-26-21	Concrete-Grey
DECK-2 Lab ID # 9092-00059-003	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Calc, Other m.p.	Concrete - bridge surface deck
		3) 5-20-21 4) May-26-21	Concrete-Grey
DECK-3 Lab ID # 9092-00059-004	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Calc, Other m.p.	Concrete - bridge surface deck
		3) 5-20-21 4) May-26-21	Concrete-Grey
ABUT-1 Lab ID # 9092-00059-005	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Red-dyed concrete - abutment
		3) 5-20-21 4) May-26-21	Concrete-Red
ABUT-2 Lab ID # 9092-00059-006	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Red-dyed concrete - abutment
		3) 5-20-21 4) May-26-21	Concrete-Red
ABUT-3 Lab ID # 9092-00059-007	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Red-dyed concrete - abutment
		3) 5-20-21 4) May-26-21	Concrete-Red
PARA-1 Split A Lab ID # 9092-00059-008A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Gyp, Other	White coated and exposed concrete - parapet
		3) 5-20-21 4) May-26-21	Coating-White
PARA-1 Split B Lab ID # 9092-00059-008B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	White coated and exposed concrete - parapet
		3) 4) May-26-21	Concrete-Grey
PARA-2 Split A Lab ID # 9092-00059-009A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Gyp, Other	White coated and exposed concrete - parapet
		3) 5-20-21 4) May-26-21	Coating-White

Limit of quantitation of method is estimated to be 1% asbestos using a visual area estimation technique. Split samples are inhomogeneous.

Laboratory Analyst
Greg Hanes



NVLAP Lab Code 200104-0

POLARIZED LIGHT MICROSCOPY ANALYTICAL REPORT

EPA Method 600/R-93/116 or 600/M4-82-020

Page: 2 of 3

Contact: Robert Piekarz	Samples Indicated: 19	Report No. 144570
Address: Nevada Department of 1263 South Stewart Street Carson City, NV 89712	Reg. Samples Analyzed: 19	Date Submitted: May-25-21
	Split Layers Analyzed: 9	Date Reported: May-26-21
Job Site / No. Road milling & bridge repair EA 61010		

SAMPLE ID	ASBESTOS % TYPE	OTHER DATA	DESCRIPTION
		1) Non-Asbestos Fibers 2) Matrix Materials 3) Date/Time Collected 4) Date Analyzed	FIELD LAB
PARA-2 Split B Lab ID # 9092-00059-009B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Concrete-Grey
		3) _____ 4) May-26-21	
PARA-3 Split A Lab ID # 9092-00059-010A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Gyp, Other	White coated and exposed concrete - parapet
		3) 5-20-21 4) May-26-21	Coating-White
PARA-3 Split B Lab ID # 9092-00059-010B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Concrete-Grey
		3) _____ 4) May-26-21	
SW-1 Lab ID # 9092-00059-011	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Impressed concrete - soundwall
		3) 5-20-21 4) May-26-21	Concrete-Grey
SW-2 Lab ID # 9092-00059-012	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Impressed concrete - soundwall
		3) 5-20-21 4) May-26-21	Concrete-Grey
SW-3 Lab ID # 9092-00059-013	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Impressed concrete - soundwall
		3) 5-20-21 4) May-26-21	Concrete-Grey
BEAM-1 Split A Lab ID # 9092-00059-014A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Calc, Other	White coated concrete - bridge support slab/beam
		3) 5-20-21 4) May-26-21	Coating-White
BEAM-1 Split B Lab ID # 9092-00059-014B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	White coated concrete - bridge support slab/beam
		3) _____ 4) May-26-21	Concrete-Grey
BEAM-2 Split A Lab ID # 9092-00059-015A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Calc, Other	White coated concrete - bridge support slab/beam
		3) 5-20-21 4) May-26-21	Coating-White
BEAM-2 Split B Lab ID # 9092-00059-015B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	Concrete-Grey
		3) _____ 4) May-26-21	

Limit of quantitation of method is estimated to be 1% asbestos using a visual area estimation technique. Split samples are inhomogeneous.

Laboratory Analyst

Greg Hanes



NVLAP Lab Code 200104-0

POLARIZED LIGHT MICROSCOPY ANALYTICAL REPORT

EPA Method 600/R-93/116 or 600/M4-82-020

Page: 3 of 3

Contact: Robert Piekarz Address: Nevada Department of 1263 South Stewart Street Carson City, NV 89712	Samples Indicated: 19 Reg. Samples Analyzed: 19 Split Layers Analyzed: 9 Job Site / No. Road milling & bridge repair EA 61010	Report No. 144570 Date Submitted: May-25-21 Date Reported: May-26-21
--	---	---

SAMPLE ID	ASBESTOS % TYPE	OTHER DATA	DESCRIPTION
		1) Non-Asbestos Fibers 2) Matrix Materials 3) Date/Time Collected 4) Date Analyzed	FIELD LAB
BEAM-3 Split A Lab ID # 9092-00059-016A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Calc, Other	White coated concrete - bridge support slab/beam
		3) 5-20-21 4) May-26-21	Coating-White
BEAM-3 Split B Lab ID # 9092-00059-016B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	
		3) 4) May-26-21	Concrete-Grey
BW/WW-1 Split A Lab ID # 9092-00059-017A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Calc, Other	White coated concrete - backwall & wing walls
		3) 5-20-21 4) May-26-21	Coating-White
BW/WW-1 Split B Lab ID # 9092-00059-017B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	
		3) 4) May-26-21	Concrete-Grey
BW/WW-2 Split A Lab ID # 9092-00059-018A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Calc, Other	White coated concrete - backwall & wing walls
		3) 5-20-21 4) May-26-21	Coating-White
BW/WW-2 Split B Lab ID # 9092-00059-018B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	
		3) 4) May-26-21	Concrete-Grey
BW/WW-3 Split A Lab ID # 9092-00059-019A	None Detected	1) <1% Cellulose 2) 100-100% Bndr, Qtz, Calc, Other	White coated concrete - backwall & wing walls
		3) 5-20-21 4) May-26-21	Coating-White
BW/WW-3 Split B Lab ID # 9092-00059-019B	None Detected	1) None Detected 2) 99-100% Clay, Qtz, Gyp, Other m.p.	
		3) 4) May-26-21	Concrete-Grey
Lab ID #		1)	
		2)	
Lab ID #		3)	
		4)	

Limit of quantitation of method is estimated to be 1% asbestos using a visual area estimation technique. Split samples are inhomogeneous.

Laboratory Analyst
Greg Hanes

Survey Data

Inspectors: Robert Piekarz		Project Name: Road milling and bridge repair		Project Number: EA 61010		Date Sampled: 5/20/2021	
Phone: 888-7692		Project Location: Bridge H-1442		Analysis Type: Asbestos		Air <u>Bulk</u>	
Turn-A-Round Time: Rush		24-Hour <u>2 Day</u>		Requests: Verbal		Fax <u>EMA</u>	
Lab #	Sample ID	Material Description	Sample Location	Location of Materials	Quantity	Condition	Test to First Positive: Yes No
1	Coating	white coating/texturing materials		throughout bridge			Asbestos %
2	Deck-1	concrete		bridge surface deck			
3	Deck-2	"		"	"		
4	Deck-3	"		"	"		
5	Abut-1	red dyed concrete		abutment			
6	Abut-2	"		"	"		
7	Abut-3	"		"	"		
8	Para-1	white coated and exposed concrete		parapet			
9	Para-2	"		"	"		
10	Para-3	"		"	"		

Comments/Additional Information

MATERIAL	CONDITION	UNITS	ASBESTOS %
PFI - Pipe Fitted Insulation	G - Good	LF - Linear Feet	A - Asbestos
PRI - Pipe Run Insulation	D - Damaged	SF - Square Feet	C - Chrysotile Asbestos
DI - Duct Insulation	SD - Significant Damage	CF - Cubic Feet	NDA - No Asbestos Detected
TI - Tank Insulation			Assumed ACM - No Samples Taken
EI - Expansion Joint			
BI - Boiler Insulation			

Relinquished By: Andrew Brown ATEM Relinquished By: _____
 Date/Time: 5/25/21, 8:30 Date/Time: _____
 Received By: 9:00 AM Received By: _____

Survey Data

Inspectors: Robert Piekarz		Project Name: Road milling and bridge repair		Project Number: EA 61010		Date Sampled: 5/20/2021			
Phone: 888-7692		Project Location: Bridge H-1442		Analysis Type: Asbestos		Air			
Turn-A-Round Time: Rush		24-Hour		Requests: Verbal		Test to First Positive:			
Lab #	Sample ID	Material Description	Sample Location	Location of Materials	Quantity	Condition	Friable	Yes	No
11	SW-1	impressed concrete		soundwall					
12	SW-2	"		"					
13	SW-3 -SW-1 SAMPLE BAG	"		"					
14	Beam-1	white coated concrete		bridge support slab/beam					
15	Beam-2	"		"					
16	Beam-3	"		"					
17	BW/WW-1	white coated concrete		backwall and wing walls					
18	BW/WW-2	"		"					
19	BW/WW-3	"		"					
Comments/Additional Information									
MATERIAL				CONDITION		UNITS		ASBESTOS %	
PFI - Pipe Fitted Insulation	VT - Vinyl Tile	GA - Gasket	G - Good	LF - Linear Feet	A - Asbestos				
PBI - Pipe Run Insulation	M - Mastic	D - Debris	D - Damaged	SF - Square Feet	C - Chrysotile Asbestos				
DI - Duct Insulation	CBM - Cove Base Mastic	TSI - Thermal System Insulation	SD - Significant Damage	CF - Cubic Feet	NDA - No Asbestos Detected				
TI - Tank Insulation	AT - Acoustical Tile	R - Roof			Assumed ACM - No Samples Taken				
EI - Expansion Joint	SA - Spray Acoustic	DW - Drywall							
BI - Boiler Insulation	W - Wall	JC - Joint Compound							
Relinquished By: <u>[Signature]</u>				Relinquished By: _____					
Date/Time: <u>5/25/21, 8:30</u>				Date/Time: _____					
Received By: _____				Received By: _____					

Appendix D
Material Coating Sample(s)
Analytical Results



Alpha Analytical, Inc.
255 Glendale Ave, #21
Sparks, Nevada 89431
TEL: (775) 355-1044 FAX: (775) 355-0406
Website: www.alpha-analytical.com

June 01, 2021

Robert Piekarz
Nevada DOT Environmental (NDOT)
1263 S. Stewart St.
Carson City, NV 89712
TEL: (775) 888-7692
FAX: (775) 888-7104

RE:

Order No.: NDO2105172

Dear Robert Piekarz:

The result of this report apply to the sample(s) as received.

There were no problems with the analytical events associated with this report unless noted.

Quality control data is within laboratory defined or method specified acceptance limits except if noted.

If you have any questions regarding these tests results, please feel free to call.

Sincerely,

A handwritten signature in black ink that reads "Randy Gardner".

Randy Gardner
Laboratory Manager
255 Glendale Ave, #21
Sparks, Nevada 89431



Alpha Analytical, Inc.
255 Glendale Ave, #21
Sparks, Nevada 89431
TEL: (775) 355-1044 FAX: (775) 355-0406
Website: www.alpha-analytical.com

Analytical Report

WO#: NDO2105172

Report Date: 6/1/2021

CLIENT: Nevada DOT Environmental (NDOT)

Collection Date: 5/20/2021 12:00:00 PM

Project:

Lab ID: 2105172-01

Matrix: OTHER

Client Sample ID: H-1442 TEXT

Analyses	Result	RL	Qual	Units	Date Analyzed	Method
Chromium (Cr)	20	1.0		mg/Kg	5/28/2021	Metals by EPA 6020
Arsenic (As)	ND	1.0		mg/Kg	5/28/2021	Metals by EPA 6020
Selenium (Se)	ND	2.0		mg/Kg	5/28/2021	Metals by EPA 6020
Silver (Ag)	ND	1.0		mg/Kg	5/28/2021	Metals by EPA 6020
Cadmium (Cd)	ND	1.0		mg/Kg	5/28/2021	Metals by EPA 6020
Barium (Ba)	620	1.0		mg/Kg	5/28/2021	Metals by EPA 6020
Lead (Pb)	10	1.0		mg/Kg	5/28/2021	Metals by EPA 6020



Alpha Analytical, Inc.
 255 Glendale Ave, #21
 Sparks, Nevada 89431
 TEL: (775) 355-1044 FAX: (775) 355-0406
 Website: www.alpha-analytical.com

QC SUMMARY REPORT

WO#: 2105172

01-Jun-21

Client: Nevada DOT Environmental (NDOT)

Project:

TestCode: METALS_SO

Sample ID: MB-13026	SampType: MBLK	TestCode: METALS_SO	Units: mg/Kg
Client ID: PBS	Batch ID: 13026	TestNo: E200.8	
Prep Date: 5/27/2021	RunNo: 11643	SeqNo: 325987	
Analysis Date: 5/28/2021			

Analyte	Result	PQL	SPK Value	SPK Ref Val	%REC	LowLimit	HighLimit	RPD Ref Val	%RPD	RPDLimit	Qual
Chromium (Cr)	ND	1									
Arsenic (As)	ND	1									
Selenium (Se)	ND	2									
Silver (Ag)	ND	1									
Cadmium (Cd)	ND	1									
Barium (Ba)	ND	1									
Lead (Pb)	ND	1									

Sample ID: LCS-13026	SampType: LCS	TestCode: METALS_SO	Units: mg/Kg
Client ID: LCSS	Batch ID: 13026	TestNo: E200.8	
Prep Date: 5/27/2021	RunNo: 11643	SeqNo: 325988	
Analysis Date: 5/28/2021			

Analyte	Result	PQL	SPK Value	SPK Ref Val	%REC	LowLimit	HighLimit	RPD Ref Val	%RPD	RPDLimit	Qual
Chromium (Cr)	50.5	1	50	0	101	79.51	120.49				
Arsenic (As)	50.9	1	50	0	102	79.51	120.49				
Selenium (Se)	51.6	2	50	0	103	79.51	120.49				
Silver (Ag)	47.4	1	50	0	94.8	79.51	120.49				
Cadmium (Cd)	45.7	1	50	0	91.5	79.51	120.49				
Barium (Ba)	50.7	1	50	0	101	79.51	120.49				
Lead (Pb)	50	1	50	0	99.9	79.51	120.49				

Sample ID: 2105182-01AMSD	SampType: MSD	TestCode: METALS_SO	Units: mg/Kg
Client ID: BatchQC	Batch ID: 13026	TestNo: E200.8	
Prep Date: 5/27/2021	RunNo: 11643	SeqNo: 325991	
Analysis Date: 5/28/2021			

Analyte	Result	PQL	SPK Value	SPK Ref Val	%REC	LowLimit	HighLimit	RPD Ref Val	%RPD	RPDLimit	Qual
Chromium (Cr)	74.1	1	50	22	104	69.51	130.49	75.1	1.4	20	
Arsenic (As)	61.3	1	50	7.9	107	69.51	130.49	59.5	3	20	
Selenium (Se)	52.9	2	50	0	106	69.51	130.49	54.7	3.4	20	
Silver (Ag)	51.4	1	50	0	103	69.51	130.49	50.8	1.1	20	
Cadmium (Cd)	50.8	1	50	0	102	69.51	130.49	50.4	0.83	20	
Barium (Ba)	394	1	50	310	169	69.51	130.49	312	23	20	RS
Lead (Pb)	62.9	1	50	11.2	104	69.51	130.49	63.8	1.5	20	

Qualifiers:
 B Analyte detected in the associated Method Blank
 ND Not Detected at the Reporting Limit
 R RPD outside accepted recovery limits
 S Spike Recovery outside accepted recovery limits



Alpha Analytical, Inc.
 255 Glendale Ave, #21
 Sparks, Nevada 89431
 TEL: (775) 355-1044 FAX: (775) 355-0406
 Website: www.alpha-analytical.com

QC SUMMARY REPORT

WO#: 2105172

01-Jun-21

Client: Nevada DOT Environmental (NDOT)

Project:

TestCode: METALS_SO

Sample ID: 2105182-01AMS	SampType: MS	TestCode: METALS_SO	Units: mg/Kg
Client ID: BatchQC	Batch ID: 13026	TestNo: E200.8	
Prep Date: 5/27/2021	RunNo: 11643	SeqNo: 325990	
Analysis Date: 5/28/2021			

Analyte	Result	PQL	SPK Value	SPK Ref Val	%REC	LowLimit	HighLimit	RPD Ref Val	%RPD	RPDLimit	Qual
Chromium (Cr)	75.1	1	50	22	106	69.51	130.49				
Arsenic (As)	59.5	1	50	7.9	103	69.51	130.49				
Selenium (Se)	54.7	2	50	0	109	69.51	130.49				
Silver (Ag)	50.8	1	50	0	102	69.51	130.49				
Cadmium (Cd)	50.4	1	50	0	101	69.51	130.49				
Barium (Ba)	312	1	50	310	4.36	69.51	130.49				S
Lead (Pb)	63.8	1	50	11.2	105	69.51	130.49				

Qualifiers: B Analyte detected in the associated Method Blank
 ND Not Detected at the Reporting Limit
 R RPD outside accepted recovery limits
 S Spike Recovery outside accepted recovery limits



Alpha Analytical, Inc.
255 Glendale Ave, #21
Sparks, Nevada 89431
TEL: (775) 355-1044 FAX: (775) 355-0406
Website: www.alpha-analytical.com

Definition Only

WO#: 2105172
Date: 6/1/2021

Definitions:

ND = Not Detected

C = Reported concentration includes additional compounds uncharacteristic of common fuels and lubricants.

D = Reporting Limits were increased due to high concentrations of non-target analytes.

H = Reporting Limits were increased due to the hydrocarbons present in the sample.

J = The analyte was positively identified; the associated numerical value is the approximate concentration of the analyte in the sample.

K = DRO concentration may include contributions from lighter-end hydrocarbons (e.g. gasoline) that elute in the DRO range.

L = DRO concentration may include contributions from heavier-end hydrocarbons (e.g. motor oil) that elute in the DRO range.

O = Reporting Limits were increased due to sample foaming.

V = Reporting Limits were increased due to high concentrations of target analytes.

X = Reporting Limits were increased due to sample matrix interferences.

Z = DRO concentration may include contributions from lighter-end (e.g. gasoline) and heavier-end (e.g. motor oil) hydrocarbons that elute in the DRO range.

S50 = The analysis of the sample required a dilution such that the surrogate concentration was diluted below the laboratory acceptance criteria. The laboratory control sample was acceptable.

S51 = Surrogate recovery could not be determined due to the presence of co-eluting hydrocarbons.

S52 = Surrogate recovery was above laboratory acceptance limits. Probable matrix effect.

S53 = Surrogate recovery was below laboratory acceptance limits. Probable matrix effect.

S54 = Surrogate recovery was below laboratory acceptance limits.

S55 = Surrogate recovery was above laboratory acceptance limits.

Report CC's Robert Piekarz

WORKORDER SUMMARY

NV

Alpha Analytical, Inc.

255 Glendale Ave, #21 Sparks, Nevada 89431

TEL: (775) 355-1044 FAX: (775) 355-0406

WorkOrder: NDO2105172

Report Due By: 09-Jun-21

EDD Required: NO

Report Attention: Robert Piekarz

Client:

Nevada DOT Environmental (NDOT)
1263 S. Stewart St.
Carson City, NV 89712

TEL: 7758887692


FAX: 7758887104

ProjectNo:

Date Received: 25-May-21

Alpha Sample ID	Client Sample ID	Matrix	Collection Date	No. of Bottles			Requested Tests						Sample Remarks		
				Alpha	Sub	TAT	METALS_SO								
NDO2105172-01	H-1442 TEXT	OTHER	5/20/2021 12:00:00 PM	1	0	10	A - As, Ba, Cd, Cr, Pb, Ag, Se								

Comments: Paint Chips

Logged in by:	Signature	Print Name	Company	Date/Time
		Haylee Tilton	Alpha Analytical, Inc.	5/25/21 10:55

NOTE: Samples are discarded 60 days after sample receipt unless other arrangements are made. Hazardous samples will be returned to client or disposed of at client expense.

Bottle Type: L-Liter V-Voa S-Soil Jar O-Orbo T-Tedlar B-Brass P-Plastic OT-Other

Appendix E
Inspector Certifications
and
Licenses

mm


STATE OF NEVADA
DEPARTMENT OF BUSINESS AND INDUSTRY
DIVISION OF INDUSTRIAL RELATIONS
Occupational Safety and Health Administration
Asbestos Control Program

Certifies That Robert Piekarz
State of Nevada-DOT
is Licensed As Asbestos Abatement Consultant

License No. IJ-1049

Expiration Date 11/24/2021

Signature Of Licensee _____



STATE OF NEVADA
DEPARTMENT OF BUSINESS AND INDUSTRY
DIVISION OF INDUSTRIAL RELATIONS
Occupational Safety and Health Administration
Asbestos Control Program

mm

Certifies That Robert Piekarz
State of Nevada-DOT
is Licensed As Asbestos Abatement Consultant

License No. IJ-1049 Expiration Date 11/24/2021

Signature Of Licensee _____

M & C Environmental Training

Asbestos Inspector
Refresher Training Course

Robert Piekarz

Has successfully completed the Asbestos Inspector Refresher course approved by the California Division of Occupational Safety and Health for purposes of certification required by Title 8, Article 2.7, Chapter 3.2, Section 341.16 and the accreditation required under the Toxic Substances Control Act, Title II. Conducted by M&C Environmental Training Inc., P.O. Box 6419, Concord, California Tel. # (510) 499-5646

Course Approval Number: CA-003-06

Location: Concord, California

Expiration: November 24, 2021

Dates: November 24, 2020

Director of Training: John McGinnis



Certificate Number **48309 IR**

M & C Environmental Training

Asbestos Management Planner

Refresher Training Course

Robert Piekarz

Has successfully completed the Asbestos Management Planner Refresher course approved by the California Division of Occupational Safety and Health for purposes of certification required by Title 8, Article 2.7, Chapter 3.2, Section 341.16 and the accreditation required under the Toxic Substances Control Act, Title II. Conducted by M&C Environmental Training Inc., P.O. Box 6419, Concord, California. Tel. # (510) 499 - 5646

Course Approval Number: CA-003-08

Location: Concord, California

Expiration: November 24, 2021

Dates: November 24, 2020

Director of Training: John McGinnis



Certificate Number 48327 PR